




PCT/GB 2003 / 0 0 5570



INVESTOR IN PEOPLE

The Patent Office
Concept House
Cardiff Road
Newport
South Wales
NP10 8QQ



I, the undersigned, being an officer duly authorised in accordance with Section 74(1) and (4) of the Deregulation & Contracting Out Act 1994, to sign and issue certificates on behalf of the Comptroller-General, hereby certify that annexed hereto is a true copy of the documents as originally filed in connection with the patent application identified therein.

In accordance with the Patents (Companies Re-registration) Rules 1982, if a company named in this certificate and any accompanying documents has re-registered under the Companies Act 1980 with the same name as that with which it was registered immediately before re-registration save for the substitution as, or inclusion as, the last part of the name of the words "public limited company" or their equivalents in Welsh, references to the name of the company in this certificate and any accompanying documents shall be treated as references to the name with which it is so re-registered.

In accordance with the rules, the words "public limited company" may be replaced by p.l.c., plc, P.L.C. or PLC.

Re-registration under the Companies Act does not constitute a new legal entity but merely subjects the company to certain additional company law rules.


Signed

Stephen Hordley

Dated 12 December 2003

**PRIORITY
DOCUMENT**

SUBMITTED OR TRANSMITTED IN
COMPLIANCE WITH RULE 17.1(a) OR (b)



1/77

Request for grant of a patent

(See the notes on the back of this form. You can also get an explanatory leaflet, from the Patent Office to help you fill in this form)

The Patent Office

Cardiff Road

Newport

Gwent NP9 1RH

1. Your reference CDK2061

2. Patent application number 0229684.6
(The Patent Office will fill in this part) 20 DEC 2002

3. Full name, address and postcode of the or of each applicant (underline all surnames)
RHODIA CONSUMER SPECIALTIES LIMITED
Oak House
Reeds Crescent
Watford
Hertfordshire, WD24 4QP.

Patents ADP number (if you know it)

If the applicant is a corporate body, give the country/state of its incorporation

084 867 94 001

4. Title of the invention BIODEGRADABLE POLYMERS

5. Name of your agent (if you have one) Barker Brettell
"Address for service" in the United Kingdom to which all correspondence should be sent (including the postcode)
138 Hagley Road
Edgbaston
Birmingham
B16 9PW

Patents ADP number (if you know it) 7442494002

6. If you are declaring priority from one or more earlier patent applications, give the country and the date of filing of the or of each of these earlier applications and (if you know it) the or each application number

Country	Priority application number (if you know it)	Date of Filing (day/month/year)

7. If this application is divided or otherwise derived from an earlier UK application, give the number and the filing date of the earlier application

Number of earlier application	Date of filing (day/month/year)

8. Is a statement of inventorship and of right to grant of a patent required in support of this request (Answer 'Yes' if:
a) any applicant named in part 3 is not an inventor, or
b) there is an inventor who is not named as an applicant, or
c) any named applicant is a corporate body.
See note (d)) YES

Patents Form 1/77

9. Enter the number of sheets for any of the following items you are filing with this form. Do not count copies of the same document

Continuation sheets of this form -

Description 8 + 8

Claim(s) 4 + 4

Abstract -

Drawing(s) -

10. If you are also filing any of the following, state how many against each item.

Priority documents -

Translations of priority documents -

Statement of inventorship and right to grant of a patent (*Patents Form 7/77*) -

Request for preliminary examination 1
(*Patents Form 9/77*)

Request for substantive examination -
(*Patents Form 10/77*)

Any other documents -
(*please specify*)

1. I/We request the grant of a patent on the basis of this application.

Signature

Barker Brettell

Date

Barker Brettell

19 December 2002

2. Name and daytime telephone number of person to contact in the United Kingdom

Colin D. Kinton

Tel: 0121 456 1364

Warning

After an application for a patent has been filed, the Comptroller of the Patent Office will consider whether publication or communication of the invention should be prohibited or restricted under Section 22 of the Patents Act 1977. You will be informed if it is necessary to prohibit or restrict your invention in this way. Furthermore, if you live in the United Kingdom, Section 23 of the Patents Act 1977 stops you from applying for a patent abroad without first getting written permission from the Patent Office unless an application has been filed at least 6 weeks beforehand in the United Kingdom for a patent for the same invention and either no direction prohibiting publication or communication has been given, or any such direction has been revoked.

Notes

If you need help to fill in this form or you have any questions, please contact the Patent Office on 01645 500505. Write your answers in capital letters using black ink or you may type them.

If there is not enough space for all the relevant details on any part of this form, please continue on a separate sheet of paper and write "see continuation sheet" in the relevant part(s). Any continuation sheet should be attached to this form.

If you have answered 'Yes' Patents Form 7/77 will need to be filed.

Once you have filled in the form you must remember to sign and date it.

For details of the fee and ways to pay please contact the Patent Office.

BIODEGRADABLE POLYMERS

This invention relates to biodegradable polymers, especially phosphorus-containing polymers which meet or exceed the minimum statutory requirements for biodegradability. This invention also relates to a method of making such polymers and to their use as scale-inhibitors in oilfield applications.

There is a need for more environmentally benign chemicals to be used in the extraction of petroleum from subsea reservoirs, such as those located in the North Sea. Chemicals that may ultimately be discharged to the marine environment must have low toxicity towards marine organisms and should not exhibit a tendency to build up in their tissues (bio-accumulate). It is also desirable that a product does not accumulate in the environment, but can be degraded chemically or by the action of micro-organisms (biodegradation). Thus, the authorities who regulate the use of chemicals in the North Sea stipulate a threshold of at least 20% biodegradation in 28 days (OECD 306) as part of the "pre-screening" test for the 'CHARM' model, which is currently used to assess environmental impact.

Polymers having phosphorus-containing end-caps, especially polymers comprising acrylic acid, are widely used as scale-inhibitors, particularly in oilfield applications. Examples of such polymers are disclosed in the applicant's EP-A-0 861 846, the contents of which are incorporated herein by reference.

It is known that the biodegradability of acrylic acid-containing polymers, which are generally poorly biodegraded, is greatly improved by reducing the weight average molecular weight (Mw) below 700 Daltons. See, for example, J. Environ. Polym. Degrad., 1997, 5, p41-48. It was suggested that one possible means of producing polymers with Mw in this region

might be afforded by the use of the lower oxo acids of phosphorus (III) and their salts as chain-transfer agents, but it was by no means certain that the resulting polymers would be as biodegradable as the corresponding phosphorus-free polyacrylates. Such polymers are being
5 increasingly utilised as scale inhibitors during the secondary recovery of oil from reservoirs with very demanding water chemistry and conditions, so it is important that low molecular weight modifications retain this functionality. The effect of reducing molecular weight on scale inhibitor performance is again not predictable: for simple polycarboxylates there
10 is often an optimum range of molecular weight, either side of which performance often falls off markedly.

The present invention provides, in a first aspect, a phosphorus-containing polymer comprising the reaction product of an unsaturated phosphonic
15 acid with a chain-transfer agent, the polymer having improved biodegradability as compared to the same polymer when made in the absence of the chain-transfer agent.

Preferably, the polymer has a biodegradability of at least 20% per
20 28 days (as determined by OECD 306).

The chain-transfer agent may be, for example,

- (a) benzene, toluene, ethylbenzene or chlorobenzene;
- (b) methylene chloride, ethylene chloride, chloroform or carbon
25 tetrachloride;
- (c) acetone, thiophenol, n-butyl thiol or dodecyl thiol.

We have found that by the use of chain-transfer agents containing at least one 'P-H' bond, it is possible to produce polymers which combine
30 excellent activity as oilfield scale inhibitors with good biodegradability, often in excess of that required by 'OECD 306'.

In a first preferred embodiment of the first aspect of the present invention, there is provided a phosphorus-containing polymer comprising the reaction product of a chain-transfer agent having at least one P-H
5 bond with an unsaturated carboxylic, phosphonic or sulphonic acid, the polymer having a biodegradability of at least 20% per 28 days (as determined by OECD 306).

We have also found that polymers which include phosphorus-containing
10 end-caps can have a desirably high biodegradability as well as being effective as oilfield scale inhibitors.

Thus, in a second preferred embodiment of the first aspect of the present invention, there is provided a polymer having phosphorus-containing end-
15 caps and comprising the reaction product of a chain-transfer agent having at least one P-H bond with an unsaturated carboxylic, phosphonic or sulphonic acid, said polymer having a biodegradability of at least 20% per 28 days (as determined by OECD 306).

20 Preferably, the chain-transfer agent having at least one P-H bond is hypophosphorous acid or a water-soluble salt (such as an alkali metal salt or ammonium salt) of said acid.

Preferably, the unsaturated carboxylic acid is acrylic acid or a water-
25 soluble salt of said acid.

Alternatively, the unsaturated carboxylic acid may be, for example, methacrylic acid, maleic acid, fumaric acid, itaconic acid, aconitic acid, citraconic acid, mesaconic acid, crotonic acid, isocrotonic acid, angelic
30 acid or tiglic acid (or a water-soluble salt of any of said acids).

Suitably, the unsaturated phosphonic acid is vinylphosphonic acid (VPA) or vinylidene-1,1-diphosphonic acid (VDPA) or a water-soluble salt of either of said acids.

- 5 Preferably, the unsaturated sulphonic acid is vinylsulphonic acid (VSA) or a water-soluble salt of said acid.

10 In a third preferred embodiment of the first aspect of the present invention, the polymer comprises a telomer which is the reaction product of an adduct of vinylphosphonic acid and hypophosphorous acid (hereinafter referred to as "PPE-endcapper") with acrylic acid, said telomer being hereinafter referred to as a "PPE-endcapped polyacrylate".

15 The ratio of the PPE-endcapper to acrylic acid is suitably in the range 1:5 to 1:20 molar and preferably about 1:10 molar.

20 Preferably, the polymers according to the present invention exhibit a weight average molecular weight such that at least 20% by weight of the polymer has a weight average molecular weight of 1000 or lower. More preferably, at least 35% by weight of the polymer has a weight average molecular weight of 1000 or lower.

25 In a second aspect, the present invention provides a method of making a polymer according to the first aspect of the present invention, in which the chain-transfer agent and the unsaturated acid are reacted together in the presence of a free-radical initiator.

The free-radical initiator is preferably an alkali metal persulphate (especially sodium persulphate).

Alternatively, the free-radical initiator may be an alkali metal peracetate, hydrogen peroxide, a hydroperoxide, chlorine dioxide, an alkali metal chlorate or hypochlorite, an organometallic hydride, an azo-compound (e.g. 4,4'-azo-bis-cyanovaleric acid), electrolysis, ultraviolet or other
5 ionising radiation, ultrasound, or any combination of the foregoing.

The present invention provides, in a third aspect, a polymer made by the method disclosed in the three immediately-preceding paragraphs.

10 In a fourth aspect, the present invention provides the use, as a scale-inhibitor for oilfield applications, of a polymer according to the first or third aspects of the present invention.

Preferred embodiments of the present invention will be illustrated by way
15 of the following Examples.

Example 1

A PPE-endcapped polyacrylate (Ref. KH59, ratio of PPP-endcapper to
20 acrylic acid 1:10 molar) was prepared as follows:

The reagents shown in TABLE A (below) were taken

TABLE A

Reagent	Quantity (g)	Dilution (ml water)	Formula Weight	Quantity (moles)
Acrylic acid (99%)	144	486	72	1.98
Sodium hydroxide (46-48%)	60	-	40	0.71
*PPE-endcapper (17.2%)	280	-	240	0.20
Sodium persulphate	23.8	177.4	238	0.10

*The endcapper consisted essentially of trisodium 1-phosphono-2-phosphino ethane, prepared according to the disclosure in the applicants' EP-A-0 861 846.

Half of the PPE endcapper (140 g, 0.1 mol) was charged to a 1-litre jacketed reactor, stirred and heated to 95°C.

Meanwhile, three feeds were prepared:

Feed (1) An initiator solution of sodium persulphate (23.8 g, 0.1 mol) and water (177.4 g);

Feed (2) Acrylic acid (144 g, 1.99 mol) was diluted with ice (200 g) and water (286 g). The pH was adjusted to 4 by addition of the sodium hydroxide solution (60 g of 46-48% solids, 0.71 mol). Half of this total solution ($690 \text{ g} \times \frac{1}{2} = 345 \text{ g}$) was added to the other half of the PPE endcapper (140 g, 0.10 mol) to give 485 g of Feed 2;

Feed (3) The remaining acrylate solution (345 g).

Once the reaction temperature had been reached, Feeds 1 and 2 were simultaneously started by means of separate peristaltic pumps. Feed 1 was

added over 8 hours and Feed 2 was added in at a steady rate over 4 hours. On completion of Feed 2, Feed 3 was added over 3½ hours. Therefore, the initiator Feed (1) runs for ½ hour longer than Feed 3. When all feeds had finished, the reaction was kept at reflux for a further ½ hour, then
5 allowed to cool (total reaction time = 8½ hours).

At this stage the product was at a concentration of 16.3% w/w actives. To achieve the desired concentration of 25% w/w actives (32.6% w/w solids), water (403 g) was removed by rotary evaporation.
10 (Concentrations based on 100% yield).

Example 2

Another PPE-encapped polyacrylate (Ref. KH70, ratio of PPE endcapper to acrylic acid 1:10 molar) was prepared by the method of Example 1
15 (above), except that in the preparation of Feed 2, the acrylic acid was fully neutralised with the sodium hydroxide solution, so that the reaction was carried out at pH7 instead of pH4.

20 Performance and Biodegradability Tests

The products of Example 1 and Example 2 (above), together with two comparative products, were subjected to the Tube Block Test described in our published application WO 01/57050, Example 3, and to the
25 Biodegradability Test (OECD 306). The results are set out in TABLE B (below). In each case, a PPE-encapped polyacrylate in which the PPE endcapper was trisodium 1-phosphono-2-phosphino-ethane was used.

TABLE B

Product	PPE to Acrylic acid ratio (molar)	Weight Average Molecular Weight (g/ml)	% Product with Mw below 100	Tube Block test (ppm active acid)	Bio-degradability (%per 28 days)
Comparative A (B13L1)	1:20	3994	18	120,120,120	15
Comparative B (KH71)	1:15	2680	25	100,100,120	5
Example 1 (KH59)	1:10	2598	42	120,120,120	23
Example 2 (KH70)	1:10	2116	31	100,120,120	28

- 5 It will be seen that the products of Examples 1 and 2 of the present invention each satisfied the conditions of OECD 306.

CLAIMS

1. A phosphorus-containing polymer, comprising the reaction product of an unsaturated phosphonic acid with a chain-transfer agent, the polymer having improved biodegradability as compared to the same polymer when made in the absence of the chain-transfer agent.
2. A polymer according to Claim 1, the polymer having a biodegradability of at least 20% per 28 days (as determined by OECD 306).
3. A polymer according to Claim 1, in which the chain-transfer agent is benzene, toluene, ethylbenzene or chlorobenzene.
4. A polymer according to Claim 1, in which the chain-transfer agent is methylene chloride, ethylene chloride, chloroform or carbon tetrachloride.
5. A polymer according to Claim 1, in which the chain-transfer agent is acetone, thiophenol, n-butyl thiol or dodecyl thiol.
6. A polymer according to Claim 1, comprising the reaction product of a chain-transfer agent having at least one P-H bond with an unsaturated carboxylic, phosphonic or sulphonic acid, the polymer having a biodegradability of at least 20% per 28 days (as determined by OECD 306).
7. A polymer according to Claim 6, having phosphorus-containing end-caps and comprising the reaction product of a chain-transfer agent having at least one P-H bond with an unsaturated carboxylic, phosphonic

or sulphonic acid, said polymer having a biodegradability of at least 20% per 28 days (as determined by OECD 306).

5 8. A polymer according to Claim 6 or 7, in which the chain-transfer agent having at least one P-H bond is hypophosphorous acid or a water-soluble salt of said acid.

10 9. A polymer according to Claim 8, in which the chain-transfer agent is an alkali metal salt or an ammonium salt of hypophosphorous acid.

10. A polymer according to any one of Claims 6 to 9, in which the unsaturated carboxylic acid is acrylic acid or a water-soluble salt of said acid.

15 11. A polymer according to any one of Claims 6 to 9, in which the unsaturated carboxylic acid is methacrylic acid, maleic acid, fumaric acid, itaconic acid, aconitic acid, citraconic acid, mesaconic acid, crotonic acid, isocrotonic acid, angelic acid, tiglic acid or a water-soluble salt of any of said acids.

20 12. A polymer according to Claim 1 or to any one of Claims 6 to 9, in which the unsaturated phosphonic acid is vinylphosphonic acid (VPA), vinylidene-1,1-diphosphonic acid (VDPA) or a water-soluble salt of either of said acids.

25 13. A polymer according to any one of Claims 6 to 9, in which the unsaturated sulphonic acid is vinylsulphonic acid (VSA) or a water-soluble salt of said acid.

14. A polymer according to any one of Claims 1 to 10, comprising a telomer which is the reaction product of a PPE-endcapper (as hereinbefore defined) with acrylic acid.
- 5 15. A polymer according to Claim 14, in which the ratio of the PPE-endcapper to acrylic acid is in the range 1:5 to 1:20 molar.
16. A polymer according to Claim 14 or 15, in which the ratio of the PPE-endcapper to acrylic acid is about 1:10 molar.
- 10 17. A polymer according to any one of Claims 1 to 16, in which at least 20% by weight of the polymer has a weight average molecular weight of 1000 or lower.
- 15 18. A polymer according to Claim 17, in which at least 35% by weight of the polymer has a weight average molecular weight of 1000 or lower.
19. A method of making a polymer according to any one of Claims 1 to 18, in which the chain-transfer agent and the unsaturated acid are
20 reacted together in the presence of a free-radical initiator.
20. A method according to Claim 19, in which the free-radical initiator is an alkali metal persulphate.
- 25 21. A method according to Claim 20, in which the free-radical initiator is sodium persulphate.
22. A method according to Claim 19, in which the free-radical initiator is an alkali metal peracetate, hydrogen peroxide, a hydroperoxide,
30 chlorine dioxide, an alkali metal chlorate or hypochlorite, an

organometallic hydride, an azo-compound or any two or more of the foregoing.


23. A method according to Claim 22, in which the free-radical initiator
5 is 4,4'-azo-bis-cyanovaleric acid.

24. A method according to Claim 19, in which the free-radical initiator
comprises electrolysis, ultraviolet or other ionising radiation, ultrasound
or any two or more of the foregoing.
10

25. A method of making a biodegradable polymer, substantially as
hereinbefore described with reference to the Examples.

26. A biodegradable polymer made by the method of any one of
15 Claims 19 to 25.

27. The use of a biodegradable polymer according to any one of
Claims 1 to 18 or to Claim 26 as a scale-inhibitor for oilfield
applications.
20



THE PATENT OFFICE
K
19 DEC 2003
NEWPORT

PCT Application

GB0305570

